

## TABELLA DI CONVERSIONE MESH/FEPA

### CONVERSION TABLE MESH/FEPA

**Nota:** La designazione della grana FEPA avrà un prefisso "D" per indicare il diamante e "B" per indicare il CBN

**Note:** The FEPA grit designation is prefixed with a "D" to denote diamond and a "B" to denote CBN

FEPA Grit Designation approx. size $\mu\text{m}$	U.S. MESH Designation Standard ASTME 11	FEPA Grit Designation approx. size $\mu\text{m}$	U.S. MESH Designation Standard ASTME 11
1181	16/18	301	50/60
1182	16/20	251	60/70
1001	18/20	252	60/80
851	20/25	213	70/80
852	20/30	181	80/100
711	25/30	151	100/120
712	25/35	126	120/140
601	30/35	107	140/170
602	30/40	91	170/200
501	35/40	76	200/230
502	35/45	64	230/270
426	40/45	54	270/325
427	40/50	46	325/400
356	45/50	39	400/500
357	45/60	33	500/600